

FICHE TECHNIQUE

“PCS_70” JAUNE

Product description	
Product description	K 2358 AMARILLO
Chemical composition	(Zr,Pr)SiO ₄
Physical and Chemical Characteristics	
Physical Form	Powder
Physical properties	
Sieve Residue	< 0.5 % (on 45 microns)
Average Particle Size (d50)	5.5 µm
Moisture	0.5 % according to POA_LAB04_MP
Working conditions	
Firing Temperature	<1250 °C
Use of the product	Mixed with ceramic glaze
Color properties- CIE LAB variability	
Permissible range	DE < 1.0 (of color variation from standard (CIE LAB) according POA LAB 12)
Additional information	
Safety Instructions	Check the label and MSDS
Storage time	5 years after reception, in its original package, sealed, indoor and in a temperature between 5 and 35°C
Standard packaging	25 kg ± 0,8% Plastic Bags / Industrial Bags (different types of packaging are available on request)

Siège social :
ZA Le Prouet
53 rue de la Filature
87350 PANAZOL
Tél.: 05.55.35.02.35
Site web : www.ceradel.fr